

RheoMud X

Bentonite Microparticle

RheoMud X is a specially formulated premium sodium bentonite.



Chemical:

Sodium montmorillonite form of the smectite trioctahedral swelling clays.

Typical chemical analysis (dry basis):

Silica (total)	52.4%
Crystalline Silica	<5%
Aluminium Oxide	15.6%
Ferric Oxide	12.1%
Calcium Oxide	1.8%
Magnesium Oxide	2.7%
Sodium Oxide	2.2%

Structure:

Rheogel® L.

Typical properties:

Fineness

Residue +75µm sieve (ISO 787/7) 0.7%

Rheology (API methods):

- Swelling power (BP) 1400%
 - Gel formation (BP) 99.5%
- To give apparent viscosity of 15 cP: 6.5 g/100ml
- At apparent viscosity of 15 cps: Yield 90 bbls/ton
US16 kL/tonne

Gel strength:

- Initial gel: 15 lb/100ft³
7 g/100ml
- 10 min gel: 25lb/100ft³
12 g/100ml

Moisture (80 °C), when packed 10%

Loose bulk density (ISO 787/11) 0.8 g/ml

Packed bulk density (ISO 787/11) 0.9 g/ml

pH value (ISO 787/9) 10

Specific Gravity 2.3 g/ml

Benefits:

- Superior engineering drilling grade bentonite
- Provides low chloride concentrations
- Enhances drilling fluid viscosity and gel strength
- Performs over a wide pH range
- Provides a suspension of high initial viscosity and gel strengths
- Contains no VOC or surfactant components to harm the environment
- Available in semi-bulk bag and bulk silo systems for ease of handling and safety.

Applications:

Drilling, grouting, civil and geotechnical.

Application and storage:

Recommended slurry concentrations:

- Slurry 0.25 - 4.5% max.

Recommended storage periods:

- Slurry 1 month
- Dry bentonite up to 5 years
- Storage of bentonite should be in a cool, dry place.

Production plant:

Certified ISO 90001: 2008.

Shipping & handling:

Rheogel® L is supplied in one tonne lots, palletized and shrink wrapped in either 1 tonne bulk or 25kg polypropylene bags.

In accordance with good industrial practice, handle with care and prevent contamination of the environment. Avoid dust formation and ignition sources. Dry bentonite spills should be swept or vacuumed. Bentonite slurry spills should be contained with an inert material and disposed of in a proper manner.

FOR INDUSTRIAL USE ONLY.

Health & safety:

This product has a low order of toxicity, and no special precautions are necessary in handling other than standard industrial protection. Detailed information on the product(s) described in this leaflet can be found in our relevant Health and Safety Information (Material Safety Data Sheet).

Registration:

Rheogel®.

Important:

The following supersedes Buyers documents. SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, tort of contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.